



Silver nanoparticles: Synthesis, Applications, and Side Effects

Shedeed¹, D. El-Shabrawy², O. Abd Eldaim³, M.A.

²Department of Biochemistry and Molecular Biology, Faculty of Veterinary Medicine, Menoufia University. ³Department of Biochemistry and Molecular Biology, Faculty of Veterinary Medicine, Menoufia University, Shebeen El-kom, Al Menoufia, Egypt,

ABSTRACT

Key words:

Silver nanoparticles, synthesis, applications, and toxicity

*Correspondence

dinak2246@gmail.com

Article History

Received: 13 Sep 2025.

Accepted: 1 Oct 2025

Silver nanoparticles (AgNPs) have garnered considerable interest recently due to their diverse applications and exceptional physicochemical properties. As AgNPs have distinct optical, electrical, catalytic, antibacterial, and antioxidant properties, they are widely used in commercial cosmetics, industrial electronics, medicinal applications such as drug delivery, wound and bone healing, biosensing, and cancer therapy, energy storage, and agricultural applications such as water filtration and treatment systems. Regardless of these benefits, AgNPs have toxic effects due to their accumulation in cellular tissues and organs, causing an increase in ROS, leading to oxidative stress, inflammation, and damage to vital organs like the liver, kidneys, spleen, and reproductive tissues. To get AgNPs' advantages, enhance biocompatibility, and mitigate their harmful effects, many strategies are applied as green synthesis methods, controlled dosage and exposure, size and shape modifications, composite nanoparticles, and surface coating. The appropriate application of AgNPs in industry and medicine depends on careful approaches that combine unique synthesis, safe delivery, and toxicity evaluation. In this review, we seek to gain a better knowledge of how to synthesize AgNPs in order to maximize their benefits while minimizing their toxicity.

1.Introduction

Nanoparticle technology is now having a significant impact on several industries due to its ability to alter material properties at the nanoscale. Apart from their industrial uses, nanoparticles are crucial in the medical field, especially for targeted drug administration [1]. Numerous NP kinds are presently under investigation across a wide range of applications. Among these, AgNPs have attracted interest because of their effective properties, particularly their antibacterial activity. They can have virucidal, fungicidal, and bactericidal impacts [2]. Because of their special optical, electrical, and antibacterial qualities, silver nanoparticles (AgNPs) are widely used in a variety of applications, such as biosensing, photonics, electronics, dental materials, cosmetics, food storage and packaging, textile coatings, catalysis, some environmental applications such as water disinfection, medical products, medical devices, antiviral coatings, and antimicrobial treatments [3]. Although AgNPs have benefits, there is growing concern about their potential harm to human health and the environment. Previous research suggests that AgNPs

may cause cytotoxicity, genetic disruption, oxidative damage, and inflammatory disorders in human cells, causing cancer, neurological issues, and respiratory infections [4]. Silver nanoparticles tend to collect in organs, including the liver, lungs, and kidneys, causing harm to cells and tissues. Some people may be allergic to AgNPs, which can result in skin irritation, rashes, and other symptoms. The tendency of AgNPs to agglomerate increases their potential for toxicity [5]. So, regulating the use and disposal of AgNPs is crucial to mitigate their environmental and human health impacts. So that researchers are exploring green synthesis methods to manufacture AgNPs from microbes or plant extracts. This approach is safer, more cost-effective, and ecologically friendlier than chemical synthesis, resulting in high-quality outcomes [6].

2.Silver nanoparticles applications

Nanotechnology is one of the key innovations that has effectively increased the utilization of silver ions. Multiple elemental ions are joined in an NP structure to create silver nanoparticles. The exceptional features of AgNPs, including their photocatalytic, optical, antiviral, antibacterial, and

anti-inflammatory qualities, have been emphasized [7]. Their biological activities are also greatly impacted by their distinct physicochemical properties, involving surface area, charge, shape, and localized surface plasmon resonance [8].




Fig 1. Characteristics of silver nanoparticles [9].

In the medical field, silver nanoparticles are used in the diagnosis of cancer cells and destroy them through photothermal treatment. Additionally, in cancer therapy, they help in targeted drug delivery for cancer treatment [10]. Silver nanoparticles have anticancer effects, as high concentrations of AgNPs induce apoptosis by increasing membrane permeability, activating caspases, and causing nuclear condensation [11]. Silver nanoparticles revealed efficient cytotoxicity against HT-29 human colon cancer cells [12]. Biosynthesized AgNPs from *Aspergillus Tereus* demonstrated significant anticancer properties, especially in the MCF-7 breast cancer cell line [13]. Utilizing AgNPs with chemotherapy can overcome radiation resistance and improve tumour treatment for several cancer types [14]. Silver nanoparticles have a strong ability to mitigate bacterial proliferation and other microbes in the following ways: rupturing of the cell wall, lysis of the cell membrane, inhibition of protein synthesis, and bacterial reproduction. As a result of these abilities, AgNPs have potent antibacterial properties against both Gram-positive and Gram-negative bacteria [15]. Numerous studies have shown that the smaller the size of NPs, the more effective the ability to penetrate the bacteria [16]. The antibacterial activity of AgNPs against *P. aeruginosa* was proved [17]. Silver nanoparticles have a great bactericidal effect on *E. coli* [18]. Silver-modified copper oxide (Ag-CuO) NPs have

antibacterial activity against Gram-positive (*S. aureus*) and Gram-negative (*E. coli*) [19]. It has been revealed that AgNPs support immune cells during inflammation, as detected in previous studies that biosynthesized AgNPs have enhanced antiviral activity against hepatitis C virus, HSV-1, and SARS-CoV-2 [20]. Direct pulmonary administration of AgNPs enhances the immune system against the influenza virus and murine pneumonia virus by activating lymphoid cells [21]. It was revealed that chemically synthesized AgNPs interacted with swine coronavirus, which inhibited viral attachment by 12% [22]. This is because AgNPs bind to virus spikes in glycoproteins without blocking virus attachment [23]. Numerous studies have shown that green-synthesized AgNPs by plant extracts increase antioxidant potential by neutralizing free radicals and mitigating oxidative stress in biological systems, as the presence of bioactive phytochemicals further boosts their antioxidant potential through a synergistic effect, leading to strong radical scavenging activity [24]. It has been shown that *Astragalus Sarcocolla* (Anzaroot) extract-mediated AgNPs exhibited antioxidant properties and had an inhibitory effect on *C. albicans* and *K. pneumonia* (25)

. Biosynthesized AgNPs from *Origanum Majorana* L. extract show potential for use in food and medicinal applications due to their potent antioxidant properties [26]. Silver nanoparticles are already being utilized in various medical applications, including coated medical equipment [27], dental materials [28], bone implants [29], and wound dressings by restoring the skin to its optimal physiological state [30].

2.Methods of Silver Nanoparticle Synthesis




Fig 2. Techniques for synthesizing AgNPs [31].

The two basic methods for creating NPs are top-down and bottom-up approaches. These methods include fundamental techniques: chemical, physical,

and biological. The physical method employs a top-down process; in contrast, the chemical and biological techniques often employ a bottom-up approach. To turn bulk materials into NPs, the top-down approach uses physical techniques such as electrical arc discharge, vapor condensation, grinding, milling, and laser ablation without chemical additions. These methods can create NPs with typical diameters between 10 and 100 nm. Nanoparticles that are physically generated usually have a consistent size and significant purity. The absence of stabilizers or capping agents, which are essential for avoiding aggregation because no potentially dangerous compounds are used, is a significant disadvantage of this approach. Atoms and molecules combine to create NPs from smaller building blocks in a bottom-up process. Some examples of bottom-up methods include chemical vapor deposition, laser pyrolysis, sol-gel processing, bioassisted synthesis, self-assembly of monomer molecules, plasma or flame spraying, and electrochemical precipitation [32].

Physical techniques usually entail creating and modifying AgNPs by applying external physical forces. These methods are highly preferred as they can generate NPs with precise size, shape, and crystallinity. They can be used for a range of biological and industrial purposes. These techniques also enable accurate control over the characteristics of NPs by modifying factors including temperature, pressure, and reaction time. Physical procedures commonly don't need complicated precursor materials or chemical reagents, which lowers the possibility of contamination and undesirable chemical byproducts, in contrast to chemical and biological processes. There are several examples of physical methods, such as vapor condensation, ball milling, sputtering, thermal decomposition, and electrospinning techniques [33]. Although chemical and physical approaches are still employed for AgNPs synthesis, there is a pressing need to deal with sustainability concerns. Chemical solvent residues such as ethylene glycol, sodium citrate, oleyl amine, and liquid paraffin are commonly found on the surface of synthesized AgNPs. When AgNPs are utilized in drug administration, antimicrobial therapies, and human-body integration applications, these chemical carriers may be dangerous. The large-scale chemical production of AgNPs isn't sustainable. There is a critical need for an eco-friendly, cost-effective, and biological (green) synthesis alternative [34].

Green synthesis approaches utilize microorganisms (fungi, yeasts, bacteria, and actinomycetes), plant resources, and templates such as membranes, viral

DNA, and diatoms [35]. Natural extracts contain phytochemical compounds such as polysaccharides, polyphenolic compounds, vitamins, amides, alkaloids, terpenoids, tannins, organic acids, and aromatic dicarboxylic acids, which are utilized to reduce Ag^+ ions to AgNPs [36]. Various plant species have been employed in the green synthesis of AgNPs, revealing the adaptability of plant-based methods. Plant metabolites differ by species, affecting the efficiency and properties of NP production. Secondary plant metabolites include flavonoids, phenolic acids, polyphenols, terpenoids, alkaloids, saponins, and tannins. The presence of hydroxyl (-OH) groups in these molecules stabilizes and reduces Ag^+ to Ag^0 , enabling the nucleation and development of AgNPs. Phenolic compounds and flavonoids are known for their ability to donate electrons, making them efficient reducing agents [37].

4.Toxicity of Silver Nanoparticles

Despite their numerous benefits in various fields, AgNPs have the potential to be harmful. The severity of toxicity of AgNPs varies based on their doses and pathways of exposure, surface coating, aggregates, form, and size; particularly, AgNPs with a smaller size are more harmful than those with a bigger size [38]. The toxicity of silver nanoparticles occurs by the production of reactive oxygen species (ROS), which can oxidize proteins and lipids and cause mitochondrial dysfunction and ribosome destabilization. Excessive ROS formation causes oxidative stress and inflammation, which can harm cell viability. Additionally, after adhesion of AgNPs to the cell membrane, they can lead to leakage of cellular components and cell death. The interaction of AgNPs with biological membranes, such as DNA, leads to genotoxicity expressed by DNA-based damage, mutations, and inhibition of transcription and replication [39]. Exposure to AgNPs has been linked to increased oxidative stress markers in liver tissues and increased lipid peroxidation. Oxidative damage can rupture cell membranes and cause the release of liver enzymes, indicating hepatocellular injury. Silver nanoparticles have been related to renal injury growth. Elevated amounts of urea and creatinine, both metabolic wastes produced by the kidneys, may indicate liver and renal failure. The liver converts ammonia, a toxic byproduct of protein breakdown, into urea through the urea cycle [40]. Silver nanoparticles produce ROS, causing cellular component damage and inflammation. Oxidative stress activates stress response pathways, leading to cell death. Animals exposed to AgNPs showed elevated lipid peroxidation indicators in their spleens [41].

Furthermore, AgNPs can destroy the endoplasmic reticulum, which can alter the structure of liver tissue and affect organ function and metabolism [42]. Additionally, lysosome frequency may rise as a result of AgNPs exposure, reflecting cellular disintegration or repair mechanisms in reaction to stress or injury from the nanoparticles [43].

5-How to reduce the side effects of Ag NPs

To limit environmental and human health risks while harnessing their positive qualities, future studies should examine the elements that influence AgNPs' toxicity and the underlying mechanisms. Understanding toxicity pathways is critical for safe use in the future [44]. The toxicity of AgNPs has been decreased using a variety of techniques. These include applying biocompatible coatings to the surface, controlling their size and form, using biodegradable materials, choosing safe and neutral core materials, conducting extensive toxicity tests, and managing dosage and exposure [45]. Green synthesis of AgNPs by using plants is one of the approaches that has been proposed to overcome the toxicity induced by AgNPs, as plant extracts are a rich source of secondary metabolites as reducing and capping agents [46]. Another efficient method for lowering AgNPs' toxicity is the modification of surface chemistry and properties [47]. Altering AgNPs' surface with biocompatible materials such as polyethylene glycol (PEG), chitosan, silica, or polyvinyl alcohol. To reduce the amount of harmful Ag^+ ions released, several changes have been made [48]. These surface modifications improve AgNPs' biocompatibility, stability, and reactivity and make them appropriate for application in biomedicine. The type of coating, particle size, and ambient conditions all affect how effective all techniques are. Aggregation and disintegration of AgNPs are inhibited by effective coating, which affects bioavailability and biological interactions [49]. Factors controlling AgNPs' toxicity, including size, shape, dosage, and release, should be managed to lessen their severity [50]. Additionally, administration of antioxidants mitigates the toxic effect of AgNPs, as they are capable of protecting various biological systems against oxidative damage by scavenging and neutralizing free radicals and reactive oxygen and nitrogen species and repairing new antioxidants. Exogenous nonenzymatic antioxidants, including mineral elements, vitamins, dietary supplements, and plant antioxidants, play a crucial role in supporting the human defence system and preventing oxidative stress-induced damage. Long-term usage of high doses of antioxidant supplements (vitamins A, C, and E, quercetin, curcumin, N-acetylcysteine, and β -carotene) may be

applied to reduce the toxicity of AgNPs [51]. Vitamin C, a natural antioxidant scavenger, can neutralize intracellular ROS, reducing lipid oxidation and mitochondrial permeability. It plays an important role in protecting cells from oxidative damage and decreasing the toxic impacts of AgNPs [52]. Vitamin E supplementation had beneficial protective effects against AgNPs' toxicity and apoptotic alterations in the tongue papillae due to its ability to neutralize ROS and reduce lipid peroxidation occurring within the body [53]. In another study, it has been proven that increased vitamin E dosages were able to restore all essential parameters and considerably shield the body from AgNPs' effect [54]. Usage of curcumin for the synthesis of biosynthesized AgNPs elevated the antibacterial and antibiofilm activities and reduced the toxic effect of AgNPs [55].

5-Conclusion

In conclusion, silver nanoparticles (AgNPs) are a versatile and promising substance with numerous applications in biomedicine, agriculture, environmental pollution control, and industry due to their broad-spectrum antibacterial, anticancer, and biological properties. However, AgNPs' exposure without control is accompanied by toxic hazards such as oxidative stress, DNA damage, hepatotoxicity, nephrotoxicity, and neurotoxicity resulting from the generation of excessive ROS. Green synthesis, surface coating, dosage and size control, co-administration with antioxidants, and targeted delivery can significantly reduce the negative effects of AgNPs. These techniques reduce cytotoxicity, improve nanoparticle stability, and increase therapeutic efficacy. Researchers may fully exploit their potential while protecting human health and the environment by prioritizing biocompatibility and sustainability in the creation and utilization of silver nanoparticles.

2. References

1. Yadav, V.K., Malik, P., Khan, A.H., Pandit, P.R., Hasan, M.A., Cabral-Pinto, M.M., Islam, S., Suriyaprabha, R., Yadav, K.K., Dinis, P.A. and Khan, S.H., 2021. Recent advances on properties and utility of nanomaterials generated from industrial and biological activities. *Crystals*, 11(6), p.634.
1. Bamel, D., Singh, A., Chaudhary, G., Kumar, M., Singh, M., Rani, N., Mundlia, P. and Sehrawat, A.R., 2021. Silver nanoparticles biosynthesis, characterization, antimicrobial activities, applications, cytotoxicity and safety issues: An updated review. *Nanomaterials*, 11(8), p.2086.

2. Madhukriti, Roy, A., Pandit, S., Kumar, A., Sharma, K., Raj, S., Raja, V. and Setyawan, H.Y., 2025. Ag-Based Nanoparticle Synthesis and Its Applications. *BioNanoScience*, 15(3), p.351.
3. Rosário, F., Hoet, P., Nogueira, A.J.A., Santos, C. and Oliveira, H., 2018. Differential pulmonary in vitro toxicity of two small-sized polyvinylpyrrolidone-coated silver nanoparticles. *Journal of Toxicology and Environmental Health, Part A*, 81(15), pp.675-690.
4. Béltéky, P., Rónavári, A., Igaz, N., Szerencsés, B., Tóth, I.Y., Pfeiffer, I., Kiricsi, M. and Kónya, Z., 2019. Silver nanoparticles: Aggregation behavior in biorelevant conditions and its impact on biological activity. *International journal of nanomedicine*, pp.667-687.
5. Rodríguez-Félix, F., Graciano-Verdugo, A.Z., Moreno-Vásquez, M.J., Lagarda-Díaz, I., Barreras-Urbina, C.G., Armenta-Villegas, L., Olguín-Moreno, A. and Tapia-Hernández, J.A., 2022. Trends in Sustainable Green Synthesis of Silver Nanoparticles Using Agri-Food Waste Extracts and Their Applications in Health. *Journal of Nanomaterials*, 2022(1), p.8874003.
6. Eker, F., Duman, H., Akdaşçi, E., Bolat, E., Sarıtaş, S., Karav, S. and Witkowska, A.M., 2024. A comprehensive review of nanoparticles: from classification to application and toxicity. *Molecules*, 29(15), p.3482.
7. Wei, L., Lu, J., Xu, H., Patel, A., Chen, Z.S. and Chen, G., 2015. Silver nanoparticles: synthesis, properties, and therapeutic applications. *Drug discovery today*, 20(5), pp.595-601.
8. Galatage, S.T., Hebalkar, A.S., Dhobale, S.V., Mali, O.R., Kumbhar, P.S., Nikade, S.V. and Killedar, S.G., 2021. Silver nanoparticles: properties, synthesis, characterization, applications and future trends. In *Silver micro-nanoparticles-properties, synthesis, characterization, and applications*. IntechOpen.
9. Miranda, R.R., Sampaio, I. and Zucolotto, V., 2022. Exploring silver nanoparticles for cancer therapy and diagnosis. *Colloids and Surfaces B: Biointerfaces*, 210, p.112254.
10. Heldt, C.L., Zahid, A., Vijayaragavan, K.S. and Mi, X., 2017. Experimental and computational surface hydrophobicity analysis of a non-enveloped virus and proteins. *Colloids and Surfaces B: Biointerfaces*, 153, pp.77-84.
11. Venkatadri, B., Shanparvish, E., Rameshkumar, M.R., Arasu, M.V., Al-Dhabi, N.A., Ponnusamy, V.K. and Agastian, P., 2020. Green synthesis of silver nanoparticles using aqueous rhizome extract of *Zingiber officinale* and *Curcuma longa*: In-vitro anti-cancer potential on human colon carcinoma HT-29 cells. *Saudi Journal of Biological Sciences*, 27(11), pp.2980-2986.
12. Xu, Z., Feng, Q., Wang, M., Zhao, H., Lin, Y. and Zhou, S., 2020. Green biosynthesized silver nanoparticles with aqueous extracts of ginkgo biloba induce apoptosis via mitochondrial pathway in cervical cancer cells. *Frontiers in oncology*, 10, p.575415.
13. Singh, P., Pandit, S., Balusamy, S.R., Madhusudan, M., Singh, H., Amsath Haseef, H.M. and Mijakovic, I., 2025. Advanced nanomaterials for cancer therapy: gold, silver, and iron oxide nanoparticles in oncological applications. *Advanced Healthcare Materials*, 14(4), p.2403059.
14. Alharbi, N.S., Alsubhi, N.S. and Felimban, A.I., 2022. Green synthesis of silver nanoparticles using medicinal plants: Characterization and application. *Journal of Radiation Research and Applied Sciences*, 15(3), pp.109-124.
15. Menichetti, A., Mavridi-Printezi, A., Mordini, D. and Montalti, M., 2023. Effect of size, shape and surface functionalization on the antibacterial activity of silver nanoparticles. *Journal of Functional Biomaterials*, 14(5), p.244.
16. Al-Momani, H., Almasri, M., Al Balawi, D.A., Hamed, S., Albiss, B.A., Aldabaibeh, N., Ibrahim, L., Albalawi, H., Al Haj Mahmoud, S., Khasawneh, A.I. and Kilani, M., 2023. The efficacy of biosynthesized silver nanoparticles against *Pseudomonas aeruginosa* isolates from cystic fibrosis patients. *Scientific reports*, 13(1), p.8876.
17. Idris, N.U., Faruk, F.U., Yerima, M.I. and Isa, A.K., 2024. Recent advances in the delivery, mechanism of action and antibacterial activity of silver nanoparticles. *UMYU Journal of Microbiology Research*, 9(3), pp.104-121.
18. Udawant, T., Thorat, P., Thapa, P., Patel, M., Shekhawat, S., Patel, R., Sudhir, A., Hudka, O., Pulidindi, I.N. and Deokar, A., 2024. Antibacterial Activity of Silver-Modified CuO Nanoparticle-Coated Masks. *Bioengineering*, 11(12), p.1234.
19. Mosidze, E., Franci, G., Dell'Annunziata, F., Capuano, N., Colella, M., Salzano, F., Galdiero, M., Bakuridze, A. and Folliero, V., 2025. Silver Nanoparticle-Mediated Antiviral Efficacy against Enveloped Viruses: A Comprehensive Review. *Global Challenges*, 9(5), p.2400380.
20. Martín-Faivre, L., Prince, L., Cornu, C., Villeret, B., Sanchez-Guzman, D., Rouzet, F., Sallenave, J.M. and Garcia-Verdugo, I., 2025. Pulmonary delivery of silver nanoparticles prevents influenza infection by recruiting and activating lymphoid cells. *Biomaterials*, 312, p.122721.

21. Wang, D., Yin, C., Bai, Y., Zhou, M., Wang, N., Tong, C., Yang, Y. and Liu, B., 2024. Chitosan-modified AgNPs efficiently inhibit swine coronavirus-induced host cell infections via targeting the spike protein. *Biomolecules*, 14(9), p.1152.
22. Salleh, A., Naomi, R., Utami, N.D., Mohammad, A.W., Mahmoudi, E., Mustafa, N. and Fauzi, M.B., 2020. The potential of silver nanoparticles for antiviral and antibacterial applications: A mechanism of action. *Nanomaterials*, 10(8), p.1566.
23. Sagar, P.V., Ramadevi, D., Basavaiah, K. and Botsa, S.M., 2024. Green synthesis of silver nanoparticles using aqueous leaf extract of *Saussurea obvallata* for efficient catalytic reduction of nitrophenol, antioxidant, and antibacterial activity. *Water Science and Engineering*, 17(3), pp.274-282.
24. Bazrgaran, A., Mahmoodabadi, S., Ghasempour, A., Shafaie, E., Sahebkar, A. and Eghbali, S., 2023. Facile bio-genic synthesis of *Astragalus sarcocolla* (Anzaroot) gum extract mediated silver nanoparticles: characterizations, antimicrobial and antioxidant activities. *Plant Nano Biology*, 6, p.100052.
25. Erenler, R. and Dag, B., 2022. Biosynthesis of silver nanoparticles using *Origanum majorana* L. and evaluation of their antioxidant activity. *Inorganic and Nano-Metal Chemistry*, 52(4), pp.485-492.
26. Marassi, V., Di Cristo, L., Smith, S.G., Ortelli, S., Blosi, M., Costa, A.L., Reschiglian, P., Volkov, Y. and Prina-Mello, A., 2018. Silver nanoparticles as a medical device in healthcare settings: A five-step approach for candidate screening of coating agents. *Royal Society open science*, 5(1), p.171113.
27. Yin, I.X., Zhang, J., Zhao, I.S., Mei, M.L., Li, Q. and Chu, C.H., 2020. The antibacterial mechanism of silver nanoparticles and its application in dentistry. *International journal of nanomedicine*, pp.2555-2562.
28. Qing, Y.A., Cheng, L., Li, R., Liu, G., Zhang, Y., Tang, X., Wang, J., Liu, H. and Qin, Y., 2018. Potential antibacterial mechanism of silver nanoparticles and the optimization of orthopedic implants by advanced modification technologies. *International journal of nanomedicine*, pp.3311-3327.
29. Kalantari, K., Mostafavi, E., Afifi, A.M., Izadiyan, Z., Jahangirian, H., Rafiee-Moghaddam, R. and Webster, T.J., 2020. Wound dressings functionalized with silver nanoparticles: promises and pitfalls. *Nanoscale*, 12(4), pp.2268-2291.
30. Dhaka, A., Mali, S.C., Sharma, S. and Trivedi, R., 2023. A review on biological synthesis of silver nanoparticles and their potential applications. *Results in Chemistry*, 6, p.101108.
31. Nguyen, N.P.U., Dang, N.T., Doan, L. and Nguyen, T.T.H., 2023. Synthesis of silver nanoparticles: from conventional to 'modern' methods—a review. *Processes*, 11(9), p.2617.
- Jagdeo K.R. Physical methods for synthesis of nanoparticles. In *Nanochemistry 2023 Feb 24* (pp. 66-76). CRC Press.
32. Jagdeo, K.R., 2023. Physical methods for synthesis of nanoparticles. In *Nanochemistry* (pp. 66-76). CRC Press.
33. Mamataj, S., Roy, S., Ravindiran, G., Datta, D. and Das, B., 2025. Contemporary research on synthesis of silver nanoparticles and its applications. *Indian Chemical Engineer*, 67(1), pp.91-120.
34. Bhatt, S. and Saraswat, S., 2024. A review on phytochemical mediated synthesis of nanoparticles through fruits and vegetables extract and their potential applications. *Nanotechnology for Environmental Engineering*, 9(3), pp.359-374.
35. Zehra, S.H., Ramzan, K., Viskelis, J., Viskelis, P. and Balciunaitiene, A., 2025. Advancements in Green Synthesis of Silver-Based Nanoparticles: Antimicrobial and Antifungal Properties in Various Films. *Nanomaterials*, 15(4), p.252.
36. Eker, F., Akdaşçi, E., Duman, H., Bechelany, M. and Karav, S., 2025. Green synthesis of silver nanoparticles using plant extracts: A comprehensive review of physicochemical properties and multifunctional applications. *International Journal of Molecular Sciences*, 26(13), p.6222.
37. Auclair, J. and Gagné, F., 2022. Shape-dependent toxicity of silver nanoparticles on freshwater cnidarians. *Nanomaterials*, 12(18), p.3107.
38. Nie, P., Zhao, Y. and Xu, H., 2023. Synthesis, applications, toxicity and toxicity mechanisms of silver nanoparticles: A review. *Ecotoxicology and Environmental Safety*, 253, p.114636.
39. Olugbodi, J.O., Lawal, B., Bako, G., Onikanni, A.S., Abolenin, S.M., Mohammud, S.S., Ataya, F.S. and Batiha, G.E.S., 2023. Effect of sub-dermal exposure of silver nanoparticles on hepatic, renal and cardiac functions accompanying oxidative damage in male Wistar rats. *Scientific reports*, 13(1), p.10539.
40. Yousef, H.N., Ibrahim, S.S., Ramadan, R.A. and Aboelwafa, H.R., 2022. The ameliorative role of eugenol against silver nanoparticles-induced hepatotoxicity in male Wistar rats. *Oxidative Medicine and Cellular Longevity*, 2022(1), p.3820848.

41. Al-Doaiss, A., Jarrar, Q. and Moshawih, S., 2020. Hepatic histopathological and ultrastructural alterations induced by 10 nm silver nanoparticles. *IET nanobiotechnology*, 14(5), pp.405-411.
42. Albadawi, E.A., Musa, E.N.A., Ghaban, H.M., Ebrahim, N.A., Albadrani, M.S. and El-Tokhy, A.I., 2024. Eco-friendly green synthesis of silver nanoparticles from guajava leaves extract for controlling organophosphorus pesticides hazards, characterization, and in-vivo toxicity assessment. *BMC Pharmacology and Toxicology*, 25(1), p.98.
43. Almatroudi, A., 2024. Unlocking the potential of silver nanoparticles: from synthesis to versatile bio-applications. *Pharmaceutics*, 16(9), p.1232.
44. Gao, J., Li, R., Wang, F., Liu, X., Zhang, J., Hu, L., Shi, J., He, B., Zhou, Q., Song, M. and Zhang, B., 2017. Determining the cytotoxicity of rare earth element nanoparticles in macrophages and the involvement of membrane damage. *Environmental Science & Technology*, 51(23), pp.13938-13948.
45. Dubey, R.K., Shukla, S. and Hussain, Z., 2023. Green synthesis of silver nanoparticles; A sustainable approach with diverse applications. *Zhongguo Ying Yong Sheng Li Xue Za Zhi*, 39, p.e20230007.
46. Samal, D., Khandayataray, P., Sravani, M. and Murthy, M.K., 2024. Silver nanoparticle ecotoxicity and phytoremediation: a critical review of current research and future prospects. *Environmental Science and Pollution Research*, 31(6), pp.8400-8428.
47. Ul-Islam, M., Alabbosh, K.F., Manan, S., Khan, S., Ahmad, F. and Ullah, M.W., 2024. Chitosan-based nanostructured biomaterials: Synthesis, properties, and biomedical applications. *Advanced Industrial and Engineering Polymer Research*, 7(1), pp.79-99.
48. He, Q., Lu, J., Liu, N., Lu, W., Li, Y., Shang, C., Li, X., Hu, L. and Jiang, G., 2022. Antiviral properties of silver nanoparticles against SARS-CoV-2: effects of surface coating and particle size. *Nanomaterials*, 12(6), p.990.
49. Abbasi, R., Shineh, G., Mobarak, M., Doughty, S. and Tayebi, L., 2023. Structural parameters of nanoparticles affecting their toxicity for biomedical applications: a review. *Journal of Nanoparticle Research*, 25(3), p.43.
50. Flieger, J., Flieger, W., Baj, J. and Maciejewski, R., 2021. Antioxidants: Classification, natural sources, activity/capacity measurements, and usefulness for the synthesis of nanoparticles. *Materials*, 14(15), p.4135.
51. Taghyan, S.A., Messiry, H.E. and Zainy, M.A.E., 2020. Evaluation of the toxic effect of silver nanoparticles and the possible protective effect of ascorbic acid on the parotid glands of albino rats: An in vivo study. *Toxicology and Industrial Health*, 36(6), pp.446-453.
52. Zaki, N.T., Al Ankily, M., Amin, R.M. and Halawa, A.M., 2020. The possible protective role of vitamin e on the induced silver nanoparticles toxicity on filiform and circumvallate tongue papillae of albino rats histological and immunohistochemical study.
53. Hedayati, S.A., Farsani, H.G., Naserabad, S.S., Hoseinifar, S.H. and Van Doan, H., 2019. Protective effect of dietary vitamin E on immunological and biochemical induction through silver nanoparticles (AgNPs) inclusion in diet and silver salt (AgNO₃) exposure on Zebrafish (Danio rerio). *Comparative Biochemistry and Physiology Part C: Toxicology & Pharmacology*, 222, pp.100-107.
54. Abdelwahab, M.A., Nabil, A., El-Hosainy, H., Tahway, R. and Taha, M.S., 2024. Green synthesis of silver nanoparticles using curcumin: A comparative study of antimicrobial and antibiofilm effects on *Acinetobacter baumannii* against chemical conventional methods. *Results in Chemistry*, 7, p.101274.