

## Research article

**Nanotechnology in the Fight Against Antimicrobial Resistance: Mechanisms, Innovations, and Future Directions**Amany Abd El-Halim<sup>1</sup>, Esraa Salama Saad<sup>2</sup>, Fatimah Yousef Altoum<sup>3</sup>, Rehab Mahmoud<sup>4\*</sup><sup>1</sup> Department of Food Science and Technology, Faculty of Agriculture, Fayoum University, Fayoum 63514, Egypt<sup>2</sup> Faculty of Postgraduate Studies for Advanced Sciences, Beni-Suef University, Beni Suef 62511, Egypt<sup>3</sup> College of pharmacy, Princess Nourah bint Abdulrahman University, Riyadh 11564, Saudi Arabia<sup>4</sup> Department of Chemistry, Faculty of Science, Beni-Suef University, Beni-Suef 62511, Egypt

RECEIVED 22 March 2025

REVISED 28 April 2025

ACCEPTED 5 June 2025

ONLINE 30 June 2025

## CITATION

Abd El-Halim A. et al. (2025). Nanotechnology in the Fight against Antimicrobial Resistance: Mechanisms, Innovations, and Future Directions. Spectrum Science Journal, 2(1): 53-65

DOI: 10.21608/sasj.2025.465439

## CORRESPONDENCE

Rehab A. Mahmoud

Email:

[rehabkhaled@science.bsu.edu.eg](mailto:rehabkhaled@science.bsu.edu.eg)

The Scientific Association for Studies and Applied Research (SASAR)

<https://sasj.journals.ekb.eg>

## COPYRIGHT

©2025 by the authors. Submitted for possible open access publication under the terms and conditions of the Creative Commons Attribution (CC BY) license.

Spectrum Science Journal

PRINT ISSN: 3062-5068

ONLINE ISSN: 3062-5076

**Abstract:**

The review addresses the critical global health issue of antimicrobial resistance (AMR) and explores the potential of nanotechnology in developing effective antimicrobial strategies. In spite of the tremendous advancements in contemporary medicine and antimicrobial treatment, infectious illnesses produced by harmful bacteria continue to pose serious hazards to worldwide public health. Early in the 20th century, the discovery of antibiotics transformed medicine and significantly decreased the death rates linked to bacterial illnesses. It examines the synthesis methodologies, physicochemical properties, and mechanisms of action of antimicrobial nanomaterials, noting the advantages of both top-down (e.g., laser ablation, lithography) and bottom-up (e.g., biological synthesis) approaches. The review emphasizes that nanoscale materials possess unique properties that enhance their effectiveness against resistant pathogens through various mechanisms such as membrane disruption and oxidative stress. Additionally, it highlights applications of these nanomaterials in drug delivery, gene therapy, biosensing, cancer detection, water treatment, and medical device coatings.

**Keywords:** Nanotechnology, antimicrobial nanomaterials, drug resistance, nanoparticle synthesis, bottom-up approach, top-down approach, green synthesis, biomedical applications, multidrug-resistant pathogens, nanocomposites.

**Introduction**

Despite tremendous advancements in contemporary medicine and antimicrobial treatment, infectious illnesses produced by harmful bacteria continue to pose serious hazards to worldwide public health. Early in the 20th century, the discovery of antibiotics transformed medicine and significantly decreased the death rates linked to bacterial illnesses [1]. However, antimicrobial resistance (AMR) in bacterial, fungal, and viral pathogens has unintentionally accelerated due to the widespread and frequently indiscriminate use of conventional antibiotics [2]. This phenomenon, which threatens to make many life-saving medical operations obsolete and may return humanity to a pre-antibiotic period, has become one of the most urgent concerns facing modern healthcare systems worldwide [3].

According to estimates, drug-resistant infections could result in 10 million deaths per year by 2050 if treatment is not received [4]. The World Health Organization (WHO) has listed AMR as one of the top ten worldwide public health problems. Due to extended hospital stays, treatment failures, and higher death rates, AMR is estimated to have a tremendous economic impact, with healthcare expenses exceeding hundreds of billions of dollars worldwide [5]. Methicillin-resistant *Staphylococcus aureus* (MRSA), carbapenem-resistant *Enterobacteriaceae* (CRE), and multidrug-resistant *Mycobacterium tuberculosis* are among the pathogenic bacteria strains that are becoming more common in both healthcare and community settings [6]. The discovery of novel antimicrobial methods that can get around current resistance mechanisms and offer efficient therapeutic options is urgently needed in light of this concerning trend.

The manipulation and engineering of matter at dimensions between 1 and 100 nanometers is known as nanotechnology, and it has become a ground-breaking scientific field with transformative promise in many areas, especially biomedicine and therapeutic development [7]. In his groundbreaking 1959 lecture, "There's Plenty of Room at the Bottom," the visionary physicist Professor Richard Feynman laid the conceptual groundwork for nanotechnology by articulating the potential for manipulating individual atoms and molecules to create materials with previously unheard-of properties [8]. The scale at which these materials function is reflected in the name "nano," which is derived from the Greek word meaning "dwarf" or "extremely small." This is a domain where quantum mechanical effects become relevant and materials exhibit behaviors that are drastically different from their bulk counterparts [9].

The exceptionally high surface area-to-volume ratio of nanomaterials, which grows exponentially as particle size shrinks to the nanoscale, is the basic idea behind their distinctive behavior [10]. Because to this geometric feature, a much higher percentage of atoms are found at or close to the surface, which improves catalytic activity, reactivity, and electrical and optical properties [11]. These unique physicochemical characteristics set nanomaterials apart from traditional bulk materials and macroscale substances, such as quantum confinement effects, higher surface energy, increased chemical reactivity, and unusual optical and electronic behaviors [12, 13].

Nanotechnology has sparked the creation of novel therapeutic agents in the biomedical field that are superior to traditional medications in terms of efficacy, bioavailability, targeted specificity, and systemic toxicity [14]. The design of multifunctional platforms that may concurrently carry out diagnostic, therapeutic, and monitoring tasks is made possible by the capacity to precisely manipulate the size, shape, surface chemistry, and functional properties of nanomaterials—a notion known as "theranostics" [15]. These developments have made it possible to tackle medical issues that were previously unsolvable, such as cancer treatment, neurological conditions, heart problems, and most notably, antibiotic resistance [16].

By using methods that are essentially distinct from those of traditional antibiotics, antimicrobial nanoparticles provide a particularly promising use of nanotechnology in the fight against drug-resistant bacteria [17]. Nanomaterials exert their antimicrobial effects through multiple simultaneous mechanisms, which makes the development of resistance much more difficult than traditional antimicrobial agents, which usually target specific cellular processes (such as cell wall synthesis, protein synthesis, or nucleic acid replication) [18]. These mechanisms include direct contact-induced physical disruption of microbial cell membranes, production of reactive oxygen species (ROS) that cause oxidative stress and damage cellular components, release of antimicrobial metal ions, disruption of DNA replication and transcription, interference with cellular respiration and metabolism, and inhibition of biofilm formation [19, 20].

Compared to traditional antibiotics, the complex structure of nanoparticle-mediated antimicrobial action offers a number of tactical advantages. First, as bacteria would need to generate many concurrent alterations in order to live, the simultaneous engagement of multiple cellular targets lowers the likelihood of resistance development [21]. Second, biofilms—structured microbial populations contained in self-

produced extracellular polymeric matrices that offer defense against traditional antimicrobials and human immunological responses—can be penetrated by nanomaterials through engineering [22]. Third, targeting ligands can be added to the surface of nanoparticles to minimize off-target effects and enable targeted distribution to infection locations [23]. Fourth, drug stability, pharmacokinetics, and controlled release patterns can all be improved by using nanomaterials as carriers for traditional antibiotics [24].

Two essentially different synthetic paradigms top-down and bottom-up approaches can be used to produce antimicrobial nanomaterials, each with special benefits and drawbacks [25]. Using mechanical, thermal, or optical methods, bulk materials are physically broken down into nanoscale particles in the top-down approach, often known as the "destructive method" [26]. Mechanical milling and grinding, laser ablation, lithography, sputtering, and thermal evaporation-condensation procedures are examples of techniques [27]. Although top-down approaches can generate large amounts of nanomaterials and provide excellent control over particle size distribution, they usually require significant energy input, may introduce surface defects and structural imperfections, and frequently lack precise control over particle morphology and crystallinity [28].

The bottom-up strategy, sometimes known as the "constructive method," on the other hand, uses chemical or biological processes to assemble atoms, molecules, or molecular clusters into nanoscale structures [29]. Chemical reduction, sol-gel synthesis, chemical vapor deposition (CVD), hydrothermal and solvothermal techniques, electrochemical deposition, and biologically mediated synthesis employing microorganisms (bacteria, fungi, actinomycetes, yeasts) or plant extracts are all included in this strategy [30, 31]. The ability to create nanoparticles with few structural flaws, better control over particle size and shape, increased chemical composition uniformity, and the possibility of surface functionalization during synthesis are just a few of the clear benefits of the bottom-up approach [32]. The development of green synthesis techniques that use biological agents is especially noteworthy because they can create biocompatible nanoparticles appropriate for biomedical applications, reduce the production of hazardous waste, and provide environmentally safe substitutes for traditional chemical methods [33].

### ***Objectives of This Review***

This thorough study attempts to provide an integrative analysis of current information about antimicrobial nanomaterials, given the crucial need of creating novel antimicrobial methods to address the worldwide AMR issue and the enormous promise of nanotechnology in this sector. The particular goals of this review are:

1. To methodically investigate the basic ideas of nanotechnology and the special physicochemical characteristics that give nanoparticles their antibacterial activity
2. To offer a thorough comparison of top-down and bottom-up synthesis strategies, encompassing traditional chemical processes and cutting-edge green synthesis methods
3. To elucidate the diverse mechanisms through which nanomaterials exert antimicrobial effects against resistant pathogens
4. To review the current state of applications of antimicrobial nanomaterials in biomedical contexts, including drug delivery, biosensing, medical device coatings, and water treatment
5. To evaluate antimicrobial testing methodologies and discuss advantages and limitations of various screening protocols
6. To identify challenges, knowledge gaps, and future research directions necessary for successful clinical translation of antimicrobial nanomaterials

## Nanotechnology

Nanotechnology has become a groundbreaking area in several scientific fields, especially in biomedicine, by offering tools to create new therapeutic agents that are more effective and have lower toxicity. By manipulating materials at the nanoscale, it has made possible the development of treatments with improved efficacy and fewer side effects [34], Nanotechnology is a fast-evolving area of research with a wide range of applications across different scientific and technological domains. It involves the creation, use, and manipulation of materials at the nanoscale. The word "Nano" is derived from a Greek term meaning tiny or extremely small. In his well-known address, "There's Plenty of Room at the Bottom," physicist Professor Richard Feynman presented the concept of nanotechnology [35]. Research has been driven by the unique observable properties (chemical, physical, optical, etc.) of nanoparticles, which differ significantly from those of bulk materials [36,37]. These nanoparticles have a wide variety of applications, such as in analytical biological probes [38,39], reprography [40,41], optoelectronics [42,43], display devices [44, 45], photo catalysis [46], water treatment, and catalysis [47,48], Monitoring or analyzing conditions such as cancer cells or the development of carcinogenic cells [49,50]Antimicrobial agents or properties [51, 52], Drug delivery or drug-related applications [53], Gene delivery [54], biological sensors [55], and detecting environmentally harmful metals or chemicals [50,56].

### Synthesis of Nanoparticles.

Typically, two main approaches are used to produce nanoparticles: the "bottom-up" and "top-down" methods. The "top-down" approach involves reducing or mechanically grinding bulk materials into nanoscale particles [57]. In contrast, the "bottom-up" strategy focuses on assembling atoms and molecules at the nanoscale to create nanoparticles [54, 58].

- **Top-Down Approach.** The top-down synthesis method produces nanoparticles through a process of destruction. It begins by breaking down a large molecule into smaller pieces, which are then transformed into nanoparticles. This technique requires significant energy and extensive processing. However, its primary advantage lies in the ability to control and customize the size and shape of the nanoparticles [59]. This approach is demonstrated through methods such as laser ablation, evaporation-condensation, milling and grinding, spray pyrolysis, lithography, and other decomposition techniques [60]. A drawback of this technology is the potential for defects in the surface morphology of the nanoparticles, as their physical properties are heavily dependent on the surface structure [61].
- **Bottom-up Approach.** The bottom-up method, also known as the building-up approach, is the reverse of the top-down technique and involves assembling atoms and molecules to form various nanoparticles. Examples of this strategy include chemical reduction, sol-gel methods, chemical vapor deposition, pyrolysis, and the use of biological agents such as bacteria, fungi, algae, actinobacteria, yeast, viruses, and plants [62] In this process, nanoparticles are created chemically or biologically by organizing atoms and molecules at the nanoscale to produce nanoparticles [63]. A key advantage of the bottom-up approach is its ability to produce metallic nanoparticles with fewer defects and a more uniform chemical structure [64].

### Antimicrobial Resistance and the Need for Novel Nanomaterials.


Microbial infections remain one of the most significant health challenges worldwide, affecting millions of people and causing a wide range of diseases. Over the past decades, the misuse and overuse of antibiotics have led to the emergence of multidrug-resistant microorganisms, commonly known as

“superbugs”. These resistant strains pose a serious threat to public health, as they are often difficult to treat using conventional antibiotics.[65]

Due to the growing resistance problem, there is an urgent need to develop alternative antimicrobial agents that are effective, safe, and environmentally friendly. In this context, nanotechnology has gained increasing attention, particularly the use of nanostructured materials with antimicrobial properties. These materials can interact with microbial cells in unique ways, leading to membrane disruption, oxidative stress, or interference with metabolic functions [66].

Among various materials, conductive polymers such as polyaniline (PANI) have emerged as promising antimicrobial candidates due to their ease of synthesis, chemical stability, and potential biocidal properties. Moreover, naturally derived materials such as fish bone, which contains hydroxyapatite and organic proteins, offer an eco-friendly source for developing novel bioactive materials [67].

Combining synthetic polymers with natural materials into nanocomposites can enhance their performance by integrating the advantages of both components. Such hybrid materials can offer multifunctional properties, making them suitable for a wide range of applications beyond antimicrobial use, including cancer treatment and environmental remediation.



**Figure 1.** Nanomaterials have major potential for treating antibiotic-resistant bacterial infection [68].


### ***Conductive Polymers: Focus on Polyaniline (PANI).***

Polyaniline (PANI) is one of the most widely studied conductive polymers due to its unique combination of electrical conductivity, environmental stability, and ease of synthesis. It exists in different oxidation states, and its conductivity can be controlled through doping, making it suitable for a variety of applications in electronics, sensors, and biomedical fields [69].

Polyaniline (PANI) is a well-known conductive polymer with excellent chemical stability, ease of synthesis, and tunable electrical properties. Recent studies have revealed its potential as an antimicrobial agent due to its ability to disrupt microbial membranes, generate reactive oxygen species (ROS), and

interfere with cellular processes. These properties, along with its biocompatibility and low cost, make PANI a promising candidate for biomedical and environmental applications [70].

The antimicrobial efficiency of PANI has been reported against a wide range of pathogens, including Gram-positive and Gram-negative bacteria, as well as some fungal species. These properties, combined with its biocompatibility and low toxicity, make PANI a promising material for developing new antimicrobial systems, especially when incorporated into composite or nanostructured forms [71].



**Figure 2.** Properties of polyaniline.

### ***Thermally Treated Cuttle Fish Bone (CB) as an Inorganic Bioactive Material***

Fish bone waste, when subjected to high-temperature calcination, undergoes significant structural and chemical transformation. At elevated temperatures (around 900°C), the organic components such as collagen and proteins are completely decomposed, resulting in an ash composed mainly of inorganic minerals including calcium oxide (CaO), magnesium oxide (MgO), carbonates, and other trace oxides.

The calcined fish bone ash exhibits high surface area, porosity, and alkaline nature, which contribute to its biological activity and adsorption capabilities. Calcium and magnesium oxides, in particular, have been reported to possess antimicrobial properties due to their ability to generate reactive oxygen species (ROS), alter pH, and disrupt microbial cell walls.

Moreover, the resulting material is eco-friendly, low-cost, and sustainable, making it attractive for incorporation into composite systems aimed at antimicrobial, anticancer, or environmental applications. When combined with polymers like polyaniline, it can contribute to the formation of multifunctional nanocomposites with enhanced properties compared to each component individually.

### ***Nano Hybrid Composite of PANI and Cuttlefish Bone.***


Combining organic conductive polymers with inorganic bioactive materials can lead to the formation of hybrid nanocomposites with synergistic properties. In this study, a nanocomposite was prepared by integrating polyaniline (PANI) with thermally treated fish bone ash. The calcined bone material, rich in calcium, magnesium, and oxide-based components, provided a stable, porous matrix that enhanced the overall functionality of the composite. The resulting PANI/fish bone ash nanocomposite demonstrated improved antimicrobial activity compared to the individual components. This enhancement can be attributed to the combined effects of the conductive and oxidative properties of polyaniline and the bioactive mineral content of the fish bone ash, which together contribute to membrane disruption, ROS generation, and ion exchange with microbial cells.

In addition to its antimicrobial efficiency, the nanocomposite also showed promising potential in other applications, including anticancer activity and water treatment, highlighting its multifunctional nature. These results indicate that the engineered nanocomposite can serve as a novel, cost-effective, and environmentally friendly material for a broad range of biomedical and environmental applications.

#### ***2.1.7 Importance of Antimicrobial Materials in the Modern World.***

**Increasing Threat of Infectious Diseases:** With the rapid spread of infectious diseases and the emergence of antimicrobial resistance (AMR), the development of new antimicrobial agents has become crucial for public health [72].

• **Emerging Technologies in Material Science:** Nanotechnology has revolutionized material science by enabling the design of advanced materials with properties tailored for specific applications, including antimicrobial action. Nanomaterials can offer advantages like higher surface area, reactivity, and enhanced interactions with biological systems [73].



**Figure 3.** Potential antimicrobial applications of nanomaterials in different fields. Created with BioRender.com [74].

### ***The Role of Nanocomposites in Enhancing Material Properties.***

- **Synergy of Components:** Nanocomposites combine the best of both worlds by integrating inorganic minerals with organic polymers, resulting in enhanced mechanical, chemical, and biological properties. The presence of inorganic materials like hydroxyapatite or fish bone ash can improve mechanical strength, while organic polymers such as PANI contribute to electrical conductivity and biocidal activity.[75]
- **Potential for Multi-Functional Applications:** Due to their combined features, nanocomposites can be engineered to address multiple challenges simultaneously, such as antimicrobial resistance, cancer treatment, and water purification, which are of major concern globally.[76]

### ***Limitations of Conventional Antimicrobials.***

- **Narrow Spectrum & Side Effects:** Most conventional antibiotics have a limited spectrum of activity and can lead to side effects, such as damaging beneficial microbiota or causing allergic reactions.[77]
- **Development of Resistance:** Continuous and inappropriate use of antibiotics accelerates the development of resistant strains, reducing the effectiveness of treatment over time [78].
- **Need for Smart Solutions:** There is a need for “smart” antimicrobial materials that can target pathogens without harming a wide range of healthy tissues or the environment [79].

### ***Mechanisms of Action of Antimicrobial Nanomaterials.***

**Physical Disruption of Microbial Membranes:** Many nanomaterials act by directly disrupting microbial cell walls or membranes, leading to leakage of cellular contents and cell death, **Generation of Reactive Oxygen Species (ROS):** Some materials can induce oxidative stress inside microbial cells, damaging DNA, proteins, and lipids, **Ion Release and pH Change:** Materials like CaO or MgO can alter the surrounding pH or release metal ions that are toxic to microbes [80].

### ***Biomedical Potential of Hybrid Nanocomposites.***

- **Targeted Drug Delivery:** Polyaniline-based composites can be engineered to carry drugs or bioactive molecules, releasing them in response to specific stimuli (e.g., pH or temperature).
- **Cancer Therapy:** Some conductive polymers can be used for photothermal or electrochemical cancer treatment due to their response to light or electric fields.
- **Bone Tissue Engineering:** Calcined fish bone, being rich in calcium and phosphate, can support bone regeneration, making such composites useful in orthopedic implants or scaffolds [81].

### ***Water Treatment Applications of Bio-Nanocomposites.***

- **Removal of Microbial Contaminants:** The antimicrobial nature of the composite allows it to kill bacteria present in polluted water sources [82].
- **Adsorption of Heavy Metals and Dyes:** The porous structure of the fish bone ash can adsorb pollutants like heavy metals, nitrates, or organic dyes [83].
- **Eco-Friendly Filtration Materials:** Using natural waste-derived materials helps in creating cost-effective and sustainable filtration systems for clean water access [84].

### ***Applications of Nano Hybrid Materials.***

The synthesized nanocomposite has broad application potential:

- **Antimicrobial Action:** Effective against both Gram-positive and Gram-negative bacteria, and possibly fungi, through multiple mechanisms including ROS production, ion exchange, and membrane disruption.
- **Cancer Treatment:** Preliminary results suggest that the nanocomposite may interfere with cancer cell growth, opening new avenues for future research.
- **Water Treatment:** The composite showed high adsorption capacity for pollutants and significant antimicrobial activity in water samples, suggesting its suitability for wastewater remediation.

### ***Role of Nanomaterials in Water Treatment.***

The use of nanomaterials in wastewater remediation is gaining traction due to their:

- **High Adsorption Capacity:** The porous nature and high surface area of materials like calcined fish bone allow effective adsorption of dyes, heavy metals, and organic pollutants.
- **Antimicrobial Effect:** Direct microbial inactivation in contaminated water helps prevent disease transmission.
- **Catalytic Properties:** Some nanomaterials can act as catalysts in degradation of pollutants or conversion of toxic substances into less harmful forms.
- **Sustainability:** Utilizing natural waste materials (like fish bone) aligns with green chemistry principles and supports circular economy initiatives. These properties position hybrid nanostructures as next-generation solutions for clean water access, especially in developing regions.

### ***Biomedical and Environmental Impact.***

The multi functionality of the synthesized nanocomposite allows it to be positioned at the intersection of two critical sectors: In Biomedical Fields: The composite's antimicrobial and anticancer potential suggest future applications in wound healing, implant coatings, or localized cancer therapy. In Environmental Fields: The ability to adsorb pollutants and inactivate pathogens directly in water sources supports its application in sustainable water purification systems. Thus, such nanomaterials are not only scientifically innovative but also socially and environmentally relevant [85].

### ***Future Perspectives of Hybrid Nano Systems.***

The rapid evolution of nanotechnology opens new doors for hybrid systems like yours:

- **Smart/Responsive Systems:** Composites that respond to stimuli (pH, temperature, light) can be used in targeted therapy or real-time sensing.
- **Personalized Medicine:** Materials can be engineered to suit specific diseases or patient needs.
- **Integrated Water Treatment Units:** Embedding such nanocomposites into filters or membranes could lead to compact, efficient, and portable water purification systems.
- **Cross-Disciplinary Innovation:** Combining insights from chemistry, biology, material science, and environmental engineering enhances the impact and creativity of such research.

## Conclusion

Nanotechnology-based antimicrobial agents represent a paradigm shift in addressing the global AMR crisis. The unique properties of nanomaterials, combined with advanced synthesis and functionalization strategies, offer unprecedented opportunities for developing next-generation antimicrobial therapeutics. However, comprehensive evaluation of long-term toxicity, environmental impact, and standardization of synthesis protocols remains essential for successful clinical translation. Future research should focus on optimizing synthesis methods, understanding nanoparticle-microbe interactions at the molecular level, and developing hybrid nanosystems with synergistic antimicrobial effects.

## References

- [1] Fleming, A. (2001). On the antibacterial action of cultures of a penicillium, with special reference to their use in the isolation of *B. influenzae*. *Bulletin of the World Health Organization*, 79, 780-790.
- [2] Unemo, M., Lahra, M. M., Cole, M., Galarza, P., Ndowa, F., Martin, I., & Wi, T. (2019). World Health Organization Global Gonococcal Antimicrobial Surveillance Program (WHO GASP): review of new data and evidence to inform international collaborative actions and research efforts. *Sexual health*, 16(5), 412-425.
- [3] O'Neill, J. (2016). Tackling drug-resistant infections globally: final report and recommendations.
- [4] Hamblion, E., Saad, N. J., Greene-Cramer, B., Awofisayo-Okuyelu, A., Selenic Minet, D., Smirnova, A., World Health Organization Public Health Intelligence teams. (2023). Global public health intelligence: World Health Organization operational practices. *PLOS Global Public Health*, 3(9), e0002359.
- [5] Staff, D. (2019). Stemming the superbug tide: just a few dollars more.
- [6] CDC, A. (2019). Antibiotic resistance threats in the United States. *US Department of Health and Human Services: Washington, DC, USA*, 1, 67-100.
- [7] Feynman, R. (2011). There's plenty of room at the bottom. *Resonance: Journal of Science Education*, 16(9).
- [8] Roco, M. C. (2003). Nanotechnology: convergence with modern biology and medicine. *Current opinion in biotechnology*, 14(3), 337-346.
- [9] Jeevanandam, J., Barhoum, A., Chan, Y. S., Dufresne, A., & Danquah, M. K. (2018). Review on nanoparticles and nanostructured materials: history, sources, toxicity and regulations. *Beilstein journal of nanotechnology*, 9(1), 1050-1074.
- [10] Roduner, E. (2006). Size matters: why nanomaterials are different. *Chemical society reviews*, 35(7), 583-592.
- [11] Goyal, R. K. (2017). *Nanomaterials and nanocomposites: synthesis, properties, characterization techniques, and applications*. CRC Press.
- [12] Khan, I., Saeed, K., & Khan, I. (2019). Nanoparticles: Properties, applications and toxicities. *Arabian journal of chemistry*, 12(7), 908-931.
- [13] Rao, C. N. R., Müller, A., & Cheetham, A. K. (Eds.). (2006). *The chemistry of nanomaterials: synthesis, properties and applications*. John Wiley & Sons.
- [14] Shi, J., Kantoff, P. W., Wooster, R., & Farokhzad, O. C. (2017). Cancer nanomedicine: progress, challenges and opportunities. *Nature reviews cancer*, 17(1), 20-37.
- [15] Lim, E. K., Kim, T., Paik, S., Haam, S., Huh, Y. M., & Leec, K. (2021). Nanomaterials for theranostics: recent advances and future challenges. *Nanomaterials and Neoplasms*, 587-775.
- [16] Pelaz, B., Alexiou, C., Alvarez-Puebla, R. A., Alves, F., Andrews, A. M., Ashraf, S., & Parak, W. J. (2017). Diverse applications of nanomedicine. *ACS nano*, 11(3), 2313-2381.
- [17] Dizaj, S. M., Lotfipour, F., Barzegar-Jalali, M., Zarrintan, M. H., & Adibkia, K. (2014). Antimicrobial activity of the metals and metal oxide nanoparticles. *Materials Science and Engineering: C*, 44, 278-284.
- [18] Huh, A. J., & Kwon, Y. J. (2011). "Nanoantibiotics": a new paradigm for treating infectious diseases using nanomaterials in the antibiotics resistant era. *Journal of controlled release*, 156(2), 128-145.
- [19] Lemire, J. A., Harrison, J. J., & Turner, R. J. (2013). Antimicrobial activity of metals: mechanisms, molecular targets and applications. *Nature Reviews Microbiology*, 11(6), 371-384.
- [20] Hajipour, M. J., Fromm, K. M., Ashkarran, A. A., de Aberasturi, D. J., de Larramendi, I. R., Rojo, T., Mahmoudi, M. (2012). Antibacterial properties of nanoparticles. *Trends in biotechnology*, 30(10), 499-511.
- [21] Zasloff, M. (2002). Antimicrobial peptides of multicellular organisms. *nature*, 415(6870), 389-395.

- [22] Bjarnsholt, T., Ciofu, O., Molin, S., Givskov, M., & Høiby, N. (2013). Applying insights from biofilm biology to drug development—can a new approach be developed? *Nature reviews Drug discovery*, 12(10), 791-808.
- [23] Gupta, A., Mumtaz, S., Li, C. H., Hussain, I., & Rotello, V. M. (2019). Combatting antibiotic-resistant bacteria using nanomaterials. *Chemical Society Reviews*, 48(2), 415-427.
- [24] Hasan, N., Cao, J., Lee, J., Hlaing, S. P., Oshi, M. A., Naeem, M., ... & Yoo, J. W. (2019). Bacteria-targeted clindamycin loaded polymeric nanoparticles: Effect of surface charge on nanoparticle adhesion to MRSA, antibacterial activity, and wound healing. *Pharmaceutics*, 11(5), 236.
- [25] Iravani, S., Korbekandi, H., Mirmohammadi, S. V., & Zolfaghari, B. (2014). Synthesis of silver nanoparticles: chemical, physical and biological methods. *Research in pharmaceutical sciences*, 9(6), 385-406.
- [26] Schaming, D., & Remita, H. (2015). Nanotechnology: from the ancient time to nowadays. *Foundations of Chemistry*, 17(3), 187-205.
- [27] Ealia, S. A. M., & Saravanakumar, M. P. (2017, November). A review on the classification, characterisation, synthesis of nanoparticles and their application. In *IOP conference series: materials science and engineering* (Vol. 263, No. 3, p. 032019). IOP Publishing.
- [28] Tiwari, J. N., Tiwari, R. N., & Kim, K. S. (2012). Zero-dimensional, one-dimensional, two-dimensional and three-dimensional nanostructured materials for advanced electrochemical energy devices. *Progress in Materials Science*, 57(4), 724-803.
- [29] Gleiter, H. (2000). Nanostructured materials: basic concepts and microstructure. *Acta materialia*, 48(1), 1-29.
- [30] Thakkar, K. N., Mhatre, S. S., & Parikh, R. Y. (2010). Biological synthesis of metallic nanoparticles. *Nanomedicine: nanotechnology, biology and medicine*, 6(2), 257-262.
- [31] Ovais, M., Khalil, A. T., Raza, A., Khan, M. A., Ahmad, I., Islam, N. U., ... & Shinwari, Z. K. (2016). Green synthesis of silver nanoparticles via plant extracts: beginning a new era in cancer theranostics. *Nanomedicine*, 11(23), 3157-3177.
- [32] Makarov, V. V., Love, A. J., Sinitsyna, O. V., Makarova, S. S., Yaminsky, I. V., Taliansky, M. E., & Kalinina, N. O. (2014). "Green" nanotechnologies: synthesis of metal nanoparticles using plants. *Acta Naturae (англоязычная версия)*, 6(1 (20)), 35-44.
- [33] Mittal, A. K., Chisti, Y., & Banerjee, U. C. (2013). Synthesis of metallic nanoparticles using plant extracts. *Biotechnology advances*, 31(2), 346-356.
- [34] A. Haleem, M. Javaid, R. P. Singh, S. Rab, and R. Suman, "Applications of nanotechnology in medical field: a brief review," *Glob. Heal. J.*, vol. 7, no. 2, pp. 70–77, 2023, doi: 10.1016/j.glohj.2023.02.008.
- [35] R. P. Feynman, "There's Plenty of Room at the Bottom: An Invitation to Enter a New Field of Physics\*," *Handbook of Nanoscience, Engineering, and Technology: Third Edition*. pp. 3–12, 2012. doi: 10.1201/9781315217178-6.
- [36] M. Rai, A. Yadav, and A. Gade, "Silver nanoparticles as a new generation of antimicrobials," *Biotechnol. Adv.*, vol. 27, no. 1, pp. 76–83, 2009, doi: 10.1016/j.biotechadv.2008.09.002.
- [37] T. K. Sau and A. L. Rogach, "Nonspherical noble metal nanoparticles: Colloid-chemical synthesis and morphology control," *Adv. Mater.*, vol. 22, no. 16, pp. 1781–1804, 2010, doi: 10.1002/adma.200901271.
- [38] A. M. Brokowski C, "乳鼠心肌提取 HHS Public Access," *Physiol. Behav.*, vol. 176, no. 5, pp. 139–148, 2019, doi: 10.1021/acs.chemrev.5b00321.Nanoparticle.
- [39] C. M. Stawicki *et al.*, "Modular fluorescent nanoparticle DNA probes for detection of peptides and proteins," *Sci. Rep.*, vol. 11, no. 1, pp. 1–15, 2021, doi: 10.1038/s41598-021-99084-4.
- [40] J. F. Hamilton and R. C. Baetzold, "Catalysis by small metal clusters," *Science (80-. )*, vol. 205, no. 4412, pp. 1213–1220, 1979, doi: 10.1126/science.205.4412.1213.
- [41] S. Kumari, N. Tehri, A. Gahlaut, and V. Hooda, "Actinomycetes mediated synthesis, characterization, and applications of metallic nanoparticles," *Inorg. Nano-Metal Chem.*, vol. 51, no. 10, pp. 1386–1395, 2020, doi: 10.1080/24701556.2020.1835978.
- [42] J. Divya, A. Pramothkumar, H. J. L. Hilary, P. J. Jayanthi, and P. C. Jobe prabakar, "Impact of copper (Cu) and iron (Fe) co-doping on structural, optical, magnetic and electrical properties of tin oxide (SnO<sub>2</sub>) nanoparticles for optoelectronics applications," *J. Mater. Sci. Mater. Electron.*, vol. 32, no. 12, pp. 16775–16785, 2021, doi: 10.1007/s10854-021-06235-4.
- [43] R. Mahmoud *et al.*, "Novel anti-inflammatory and wound healing controlled released LDH-Curcumin nanocomposite via intramuscular implantation, in-vivo study," *Arab. J. Chem.*, vol. 15, no. 3, p. 103646, 2022, doi: 10.1016/j.arabjc.2021.103646.

- [44] T. Moreira *et al.*, “Processable Thiophene-Based Polymers with Tailored Electronic Properties and their Application in Solid-State Electrochromic Devices Using Nanoparticle Films,” *Adv. Electron. Mater.*, vol. 7, no. 7, pp. 1–12, 2021, doi: 10.1002/aelm.202100166.
- [44] G. Pathak *et al.*, “Analysis of photoluminescence, UV absorbance, optical band gap and threshold voltage of TiO<sub>2</sub> nanoparticles dispersed in high birefringence nematic liquid crystal towards its application in display and photovoltaic devices,” *J. Lumin.*, vol. 192, pp. 33–39, 2017, doi: 10.1016/j.jlumin.2017.06.021.
- [46] L. Fu and Z. Fu, “Plectranthus amboinicus leaf extract-assisted biosynthesis of ZnO nanoparticles and their photocatalytic activity,” *Ceram. Int.*, vol. 41, no. 2, pp. 2492–2496, 2015, doi: 10.1016/j.ceramint.2014.10.069.
- [47] J. E. Hutchison, “Greener nanoscience: A proactive approach to advancing applications and reducing implications of nanotechnology,” *ACS Nano*, vol. 2, no. 3, pp. 395–402, 2008, doi: 10.1021/nn800131j.
- [48] D. Sharma, S. Kanchi, and K. Bisetty, “Biogenic synthesis of nanoparticles: A review,” *Arab. J. Chem.*, vol. 12, no. 8, pp. 3576–3600, 2019, doi: 10.1016/j.arabjc.2015.11.002.
- [49] S. Debnath, R. S. Kumar, and M. N. Babu, “Green synthesis of metallic nanoparticles and their potential applications,” *Pharma Times*, vol. 56, no. 1, pp. 6–11, 2024, doi: 10.58532/v3bdcs18ch16.
- [50] S. Menon, R. S., and V. K. S., “A review on biogenic synthesis of gold nanoparticles, characterization, and its applications,” *Resour. Technol.*, vol. 3, no. 4, pp. 516–527, 2017, doi: 10.1016/j.reffit.2017.08.002.
- [51] F. Ameen *et al.*, “Soil bacteria *Cupriavidus* sp. mediates the extracellular synthesis of antibacterial silver nanoparticles,” *J. Mol. Struct.*, vol. 1202, 2020, doi: 10.1016/j.molstruc.2019.127233.
- [52] N. Tehri *et al.*, “Biosynthesis, characterization, bactericidal and sporocidal activity of silver nanoparticles using the leaves extract of *Litchi chinensis*,” *Prep. Biochem. Biotechnol.*, vol. 50, no. 9, pp. 865–873, 2020, doi: 10.1080/10826068.2020.1762212.
- [53] X. Li, H. Xu, Z. S. Chen, and G. Chen, “Biosynthesis of nanoparticles by microorganisms and their applications,” *J. Nanomater.*, vol. 2011, 2011, doi: 10.1155/2011/270974.
- [54] P. Golinska, M. Wypij, A. P. Ingle, I. Gupta, H. Dahm, and M. Rai, “Biogenic synthesis of metal nanoparticles from actinomycetes: biomedical applications and cytotoxicity,” *Appl. Microbiol. Biotechnol.*, vol. 98, no. 19, pp. 8083–8097, 2014, doi: 10.1007/s00253-014-5953-7.
- [55] G. Palareti *et al.*, “Comparison between different D-Dimer cutoff values to assess the individual risk of recurrent venous thromboembolism: Analysis of results obtained in the DULCIS study,” *Int. J. Lab. Hematol.*, vol. 38, no. 1, pp. 42–49, 2016, doi: 10.1111/ijlh.12426.
- [56] A. Ahmad, S. Senapati, M. I. Khan, R. Kumar, and M. Sastry, “Extracellular Biosynthesis of Monodisperse Gold Nanoparticles by a Novel Extremophilic Actinomycete, *Thermomonospora* sp. An important area of research in nanotechnology is the synthesis of nanoparticles of different chemical compositions, sizes, shapes,” no. 15, pp. 3550–3553, 2003.
- [57] R. MICHA, “乳鼠心肌提取 HHS Public Access,” *Physiol. Behav.*, vol. 176, no. 1, pp. 100–106, 2017, doi: 10.1177/0022146515594631.Marriage.
- [58] M. F. Lengke, C. Sanpawanitchakit, and G. Southam, “Biosynthesis of Gold Nanoparticles: A Review,” *Met. Nanoparticles Microbiol.*, no. May 2016, pp. 37–74, 2011, doi: 10.1007/978-3-642-18312-6\_3.
- [59] Y. Wang and Y. Xia, “0250.NanoLett.2004,4,2047.pdf,” *Nano Lett.*, vol. 4, no. 10, pp. 2047–2050, 2004.
- [60] M. Rafique, I. Sadaf, M. S. Rafique, and M. B. Tahir, “A review on green synthesis of silver nanoparticles and their applications,” *Artif. Cells, Nanomedicine Biotechnol.*, vol. 45, no. 7, pp. 1272–1291, 2017, doi: 10.1080/21691401.2016.1241792.
- [61] T. Mustapha, N. Misni, N. R. Ithnin, A. M. Daskum, and N. Z. Unyah, “A Review on Plants and Microorganisms Mediated Synthesis of Silver Nanoparticles, Role of Plants Metabolites and Applications,” *Int. J. Environ. Res. Public Health*, vol. 19, no. 2, 2022, doi: 10.3390/ijerph19020674.
- [62] S. Iravani, “Green synthesis of metal nanoparticles using plants,” *Green Chem.*, vol. 13, no. 10, pp. 2638–2650, 2011, doi: 10.1039/c1gc15386b.
- [63] M. C. M. Daniel and D. Astruc, “Refl-10(Ligand Exchang),” *Chem. Rev.*, vol. 104, no. 1, pp. 293–346, 2004.
- [64] K. N. Thakkar, S. S. Mhatre, and R. Y. Parikh, “Biological synthesis of metallic nanoparticles,” *Nanomedicine Nanotechnology, Biol. Med.*, vol. 6, no. 2, pp. 257–262, 2010, doi: 10.1016/j.nano.2009.07.002.
- [65] M. Frieri, K. Kumar, and A. Boutin, “Antibiotic resistance,” *J. Infect. Public Health*, vol. 10, no. 4, pp. 369–378, 2017, doi: 10.1016/j.jiph.2016.08.007.
- [66] D. G. J. Larsson and C. F. Flach, “Antibiotic resistance in the environment,” *Nat. Rev. Microbiol.*, vol. 20, no. 5, pp. 257–269, 2022, doi: 10.1038/s41579-021-00649-x.

- [67] H. Giri, T. J. Dowell, M. Almtiri, and C. N. Scott, "Polyaniline Derivatives and Their Applications," *Trends Dev. Mod. Appl. Polyaniline*, pp. 1–30, 2023, doi: 10.5772/intechopen.1001940.
- [68] W. Gao and L. Zhang, "Nanomaterials arising amid antibiotic resistance," *Nat. Rev. Microbiol.*, vol. 19, no. 1, pp. 5–6, 2021, doi: 10.1038/s41579-020-00469-5.
- [69] E. M. Geniès, A. Boyle, M. Lapkowski, and C. Tsintavis, "Polyaniline: A historical survey," *Synth. Met.*, vol. 36, no. 2, pp. 139–182, 1990, doi: 10.1016/0379-6779(90)90050-U.
- [70] A. N. Andriianova *et al.*, "Antibacterial properties of polyaniline derivatives," *J. Appl. Polym. Sci.*, vol. 138, no. 47, pp. 1–11, 2021, doi: 10.1002/app.51397.
- [71] S. Bhadra, D. Khastgir, N. K. Singha, and J. H. Lee, "Progress in preparation, processing and applications of polyaniline," *Prog. Polym. Sci.*, vol. 34, no. 8, pp. 783–810, 2009, doi: 10.1016/j.progpolymsci.2009.04.003.
- [72] Z. A. Boeva and V. G. Sergeyev, "Polyaniline: Synthesis, properties, and application," *Polym. Sci. - Ser. C*, vol. 56, no. 1, pp. 144–153, 2014, doi: 10.1134/S1811238214010032.
- [73] D. R. Monteiro, L. F. Gorup, A. S. Takamiya, A. C. Ruvollo-Filho, E. R. de Camargo, and D. B. Barbosa, "The growing importance of materials that prevent microbial adhesion: antimicrobial effect of medical devices containing silver," *Int. J. Antimicrob. Agents*, vol. 34, no. 2, pp. 103–110, 2009, doi: 10.1016/j.ijantimicag.2009.01.017.
- [74] C. Ortega-Nieto, N. Losada-Garcia, D. Prodan, G. Furtos, and J. M. Palomo, "Recent Advances on the Design and Applications of Antimicrobial Nanomaterials," *Nanomaterials*, vol. 13, no. 17, 2023, doi: 10.3390/nano13172406.
- [75] T. Hassan *et al.*, "Functional nanocomposites and their potential applications: A review," *J. Polym. Res.*, vol. 28, no. 2, 2021, doi: 10.1007/s10965-021-02408-1.
- [76] Asiva Noor Rachmayani, "No 主観的健康感を中心とした在宅高齢者における 健康関連指標に関する 共分散構造分析Title," p. 6, 2015.
- [77] H. Alaoui Mdarhri *et al.*, "Alternatives Therapeutic Approaches to Conventional Antibiotics: Advantages, Limitations and Potential Application in Medicine," *Antibiotics*, vol. 11, no. 12, 2022, doi: 10.3390/antibiotics11121826.
- [78] T. J. Hossain, "Methods for screening and evaluation of antimicrobial activity: A review of protocols, advantages, and limitations," *Eur. J. Microbiol. Immunol.*, vol. 14, no. 2, pp. 97–115, 2024, doi: 10.1556/1886.2024.00035.
- [79] M. A. Salam, M. Y. Al-Amin, J. S. Pawar, N. Akhter, and I. B. Lucy, "Conventional methods and future trends in antimicrobial susceptibility testing," *Saudi J. Biol. Sci.*, vol. 30, no. 3, p. 103582, 2023, doi: 10.1016/j.sjbs.2023.103582.
- [80] T. K. Giri, D. Verma, and H. R. Badwaik, "on ot Pe rs Fo tri bu tio n se nl y Fo Pe rs is tio n se nl y," no. January, pp. 44–49, 2017, doi: 10.2174/138945011666615101910.
- [81] P. Mukherjee, A. Khademhosseini, J. Seaberg, H. Montazerian, M. N. Hossen, and R. Bhattacharya, "Hybrid nanosystems for biomedical applications," *ACS Nano*, vol. 15, no. 2, pp. 2099–2142, 2021, doi: 10.1021/acsnano.0c09382.
- [82] B. Ates, S. Koytepe, A. Ulu, C. Gurses, and V. K. Thakur, "Chemistry, structures, and advanced applications of nanocomposites from biorenewable resources," *Chem. Rev.*, vol. 120, no. 17, pp. 9304–9362, 2020, doi: 10.1021/acs.chemrev.9b00553.
- [83] I. Ali, "New generation adsorbents for water treatment," *Chem. Rev.*, vol. 112, no. 10, pp. 5073–5091, 2012, doi: 10.1021/cr300133d.
- [84] C. H. Huang and S. Y. Wang, "Application of water treatment sludge in the manufacturing of lightweight aggregate," *Constr. Build. Mater.*, vol. 43, no. July 2016, pp. 174–183, 2013, doi: 10.1016/j.conbuildmat.2013.02.016.
- [85] N. E. Mastorakis, C. A. Bulucea, T. A. Oprea, C. A. Bulucea, and P. Dondon, "Environmental and health risks associated with biomedical waste management," *Int. Conf. Dev. Energy, Environ. Econ. - Proc.*, no. October 2016, pp. 287–294, 2010.